

(19)



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11)

EP 1 273 579 A1

(12)

EUROPEAN PATENT APPLICATION

published in accordance with Art. 158(3) EPC

(43) Date of publication:

08.01.2003 Bulletin 2003/02

(51) Int Cl.7: **C07D 319/12, B01D 9/02**

(21) Application number: **01917675.9**

(86) International application number:

PCT/JP01/02721

(22) Date of filing: **30.03.2001**

(87) International publication number:

WO 01/072736 (04.10.2001 Gazette 2001/40)

(84) Designated Contracting States:

**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE TR**

Designated Extension States:

AL LT LV MK RO SI

(72) Inventors:

- **EJIRI, Tetsuo**
Iwaki-shi, Fukushima 974-8232 (JP)
- **YAMANE, Kazuyuki**
Iwaki-shi, Fukushima 971-8167 (JP)
- **OTAWARA, Kentaro**
Iwaki-shi, Fukushima 974-8232 (JP)

(30) Priority: **31.03.2000 JP 2000096713**

(71) Applicant: **KUREHA KAGAKU KOGYO**

KABUSHIKI KAISHA

Chuo-ku, Tokyo 103-8552 (JP)

(74) Representative: **Uchida, Kenji et al**

**S.A. Fedit-Loriot et Autres Conseils en Propriété
Industrielle,
38, avenue Hoche
75008 Paris (FR)**

(54) METHOD FOR PURIFICATION OF CYCLIC ESTER

(57) It is an object of the present invention to provide a method of refining continuously the crystal of a crude cyclic ester effectively in a simple manner.

A method of refining a crystal of a crude cyclic ester comprises the steps of supplying the crude cyclic ester to a vertically extending cylindrical refiner (1) from an inlet (3) provided at a lower part of the refiner (1), agitating the crude cyclic ester by an agitator provided in

the refiner (1) to make the crude cyclic ester flow upwardly, refining the crystals of the crude cyclic ester by counterflow-contact between the upflowing crude cyclic ester and a downflowing melted liquid containing a refined crystal component, and taking out refined crystals of the crude cyclic ester from an outlet (4) provided at an upper part of the refiner (1).

EP 1 273 579 A1

Description

TECHNICAL FIELD

[0001] The present invention relates to a method of refining a cyclic ester. The cyclic ester is a condensation product of a dicarboxylic acid and diol, or a product made from a hydroxycarboxylic acid dimer which is made circular by dehydrate-condensation. The cyclic ester is used as a starting material for producing a polyester or polyester amide including a biodegraded polymer or medical-use polymer.

DESCRIPTION OF THE RELATED ART

[0002] It is well known that the cyclic ester is produced by depolymerizing hydroxycarboxylic acid oligomer. There are two types of crude cyclic esters produced by the conventional method. One is a cyclic ester, wherein no solvent is adhered to its crystal, and the other is a cyclic ester, wherein a high-boiling point organic solvent is adhered to its crystal. The crude cyclic esters are refined by the appropriate method for each of the crude cyclic esters.

[0003] The following references describe the manufacturing method for the first-type cyclic ester.

[0004] U.S. Patent No. 2,668,162 describes that a glycolic acid oligomer is reduced to powder and supplied slowly to a reaction vessel, in which it is depolymerized by heating under a super vacuum. Then, the produced gas is cooled for solidification into a crude cyclic ester.

[0005] U.S. Patent No. 4,727,163 describes that a large amount of polyether is block-copolymerized with a small amount of glycolic acid to make a copolymer. The copolymer is heated under a low pressure to be depolymerized. Then, the produced gas is cooled for solidification into the crude cyclic ester.

[0006] U.S. Patent No. 4,835,293 describes that a glycolic acid oligomer is heated into a liquid. The liquid is provided with a flow of nitrogen to increase the surface area so that the liquid is evaporated from the increased surface area. The evaporated gas is provided with a flow of nitrogen and cooled for solidification into a crude cyclic ester.

[0007] U.S. Patent No. 5,326,887 and WO 92/15572A1 describe that a glycolic acid oligomer is heated and depolymerized over a fixed bed catalyst system. Then, produced gas is cooled and solidified into a crude cyclic ester.

[0008] The crude cyclic esters produced by the above methods contain impurities such as a hydroxycarboxylic acid oligomer and hydroxycarboxylic acid itself. The crude cyclic esters are purified by re-crystallization using a solvent such as an isopropanol disclosed by European Patent No. 261572, a t-amyl alcohol disclosed by German Patent Publication No. 1808939, a carbon tetrachloride disclosed by German Patent Publication No. 123473904, an ethyl acetate disclosed by U.S. Pat-

ent No. 4,727,163, and an ether disclosed by Japanese Kokai No. 06-172341. A slurry of the crystal produced by the re-crystallization is separated into a solid and a liquid by filtering, cleaned by the solvent used in the re-crystallization process or an other cleaning liquid, and dried to remove the solvent or cleaning liquid, thus providing a purified crystal.

[0009] Japanese Kokai No. 09-328481 describes a method of manufacturing the second-type crude cyclic ester, in which a mixture comprising an hydroxycarboxylic acid oligomer and at least one kind of high-boiling point organic solvent having a boiling point between 230°C and 450°C is heated under normal or reduced pressure at such a temperature as to depolymerize the oligomer. The depolymerized oligomer is dissolved in the solvent until the remaining rate of the oligomer in the liquid phase reaches 0.5% or less. The heating is further continued at the above temperature to depolymerize the remaining oligomer. The produced cyclic ester is distilled out with the high-boiling point organic solvent, and the crude cyclic ester is recovered from the distilled product.

[0010] By the method, the cyclic ester is distilled with at least one organic solvent having a boiling point of 230-450°C, and the crude cyclic ester is collected by cooling the distilled product. In this case, a non-solvent may be added in the distilled product, and the solidified or crystallized cyclic ester is separated into a solid and a liquid. The thus produced crystal of the cyclic ester includes the high-boiling point organic solvent attached thereto, which is difficult to remove by the usual drying method. However, it is indispensable to remove the high-boiling point organic solvent by any method in order to obtain a dried crystal.

[0011] A conventional method to remove such a liquid as adhered to the crystal of the cyclic ester is to displace and clean the crystal with a low-boiling point cleaning liquid, such as cyclohexane or ether, and then, remove the low-boiling point cleaning liquid by drying. The drying process is performed at a temperature lower than the melting point of the crystal. Since the cyclic ester sublimates, the loss of the crystal is increased if the pressure is reduced excessively during the drying process. In addition, if necessary, the re-crystallization is performed using an ethyl acetate. Even in this case, the adhered solvent has to be removed by drying. As fully stated above, in the conventional method using the high-boiling point organic solvent, the low-boiling point cleaning liquid is indispensable to displace the liquid adhered to the crystal. As a result, the cleaning liquid waste is a mixture comprising the high-boiling point organic solvent and the low-boiling point cleaning liquid.

[0012] The method of refining the first-type of crude cyclic ester requires additional and complicated processes including the processes for drying to remove the solvent or cleaning liquid from the crystal surface, cooling to collect the solvent or cleaning liquid removed during the drying process, evaporating to separate the mix-

ture of the solvent and the cleaning liquid collected during the cooling process. The drying process is performed at a temperature lower than the melting point of the crystal. Also, since the cyclic ester sublimates, the loss of the crystal is increased under excessively reduced pressure. A solvent, such as an alcohol, may bring about ester exchange reaction with the cyclic ester, and re-crystallization is required a few times to remove the impurities caught inside the crystal.

[0013] The method of refining the second-type of crude cyclic ester also requires complicated processes including the processes for drying to remove the cleaning liquid adhered to the crystal surface, collecting the cleaning liquid removed during the drying process, and disposing to refine and collect a mixture of the high-boiling point organic solvent and low-boiling point cleaning liquid. A solvent, such as an alcohol, may bring about ester exchange reaction with the cyclic ester, and re-crystallization is required a few times to remove the impurities caught inside the crystal.

[0014] Accordingly, it is an object of the present invention to provide a method of refining the crystal of a crude cyclic ester, which is simple and applicable to both the first- and second-types of crude cyclic esters.

DISCLOSURE OF THE INVENTION

[0015] According to the present invention, crystals are refined by means of a vertically extending cylindrical refiner provided with an inlet for supplying crude cyclic ester at a lower part of the refiner, and provided with an outlet for taking out refined crystals as products at an upper part of the refiner, and provided with an agitator for agitating crude cyclic ester in the refiner.

[0016] According to the present invention, a method of refining crystals of a crude cyclic ester comprises the steps of supplying the crude cyclic ester to a vertically extending cylindrical refiner from an inlet provided at a lower part of the refiner, agitating the crude cyclic ester by an agitator provided in the refiner to make the crude cyclic ester flow upwardly, refining the crystals of the crude cyclic ester by counterflow-contact between the upflowing crude cyclic ester and a downflowing melted liquid containing a refined crystal component, and taking out refined crystals of the crude cyclic ester from an outlet provided at an upper part of the refiner.

[0017] According to the invention, the crystal of the crude cyclic ester is refined by the counterflow-contact between the upflowing crude cyclic ester and the downflowing melted liquid containing the refined crystal component in the refiner. That is, inventors have found a method that a mother liquid and impurities adhered to the crystal are cleaned off, and those that are taken inside the crystal are sweat off by the counterflow-contact.

BRIEF DESCRIPTION OF THE DRAWINGS

[0018]

5 Fig. 1(A) is a vertical section of refining equipment according to an embodiment of the present invention.

Fig. 1(B) is an enlarged section taken along line B-B in Fig. 1(A).

10 Fig. 2 is a vertical section of refining equipment according to another embodiment of the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

Cyclic ester

[0019] The cyclic ester is a condensation product comprising a dicarboxylic acid diol, or a product made from a hydroxycarboxylic acid dimer which is dehydrate-condensed and made circular. An example of the hydroxycarboxylic acid is a glycolic acid, lactaid acid, 3-hydroxycarboxylic butyric acid, 4-hydroxycarboxylic butyric acid, 3-hydroxycarboxylic valeric acid, or 3-hydroxycarboxylic caproic acid.

[0020] In order to provide a finished cyclic ester, it is necessary to refine the first type of cyclic ester or the second type of cyclic ester. The first type is cyclic ester having no solvent, the second type is cyclic ester having high-boiling point organic solvent adhered thereto. Each of the refining equipment shown in Figs. 1 and 2 is useful for both the first and second types of the cyclic esters.

[0021] Prior to explaining the method of refining, both types of refining equipments are explained as follows.

[0022] A cylindrical refiner 1 as shown in Fig. 1(A) extends vertically and is provided with an agitator 2 therein. The agitator 2 comprises, as shown in Fig. 1(B), two rotatable shafts 2A extending vertically and having a plurality of agitating fins 2B. The two rotatable shafts 2A may rotate in the same direction or in opposite directions to each other. In either case, it is preferable that the agitating fins 2B have inclination with respect to the horizontal plane so that they create an upflow of the crude cyclic ester inside the refiner 1 during the rotation of the rotatable shafts 2A. As shown in Fig. 1(B), the agitating fins 2B provided on the two rotatable shafts partly overlap each other when viewed from the top. The overlapped area of the agitating fins 2B increases the agitating capability.

[0023] The refiner 1 is provided with an inlet 3 at lower part thereof to supply a crude cyclic ester. The inlet 3 is furnished with a means for supplying the crude cyclic ester to the inside of the refiner 1, such as a screw conveyor (not shown).

[0024] The refiner 1 is also provided at an upper part thereof with an outlet 4 to take out the refined ester crystal and a means 5 for supplying a melted liquid for the

refined crystal component from the outside of the refiner 1. The means 5 is a conduit for supplying a predetermined amount of the melted liquid having an accurately known temperature.

[0025] The refiner 1 is provided with a filter 6 at a lower part thereof and an impurity outlet 7 at the bottom thereof.

[0026] The other type of refiner in Fig. 2 has the same reference numbers as those of Fig. 1.

[0027] A upright type refiner 1 in Fig. 2 is provided at a lower part thereof with an inlet 3 having a screw conveyor 3A therein to supply a crude cyclic ester including impurities and, at an upper part thereof, a melting heater 14 to melt the ester crystal. The melted liquid melted by the heater 14 are brought into counterflow-contact with the cyclic ester coming upwardly in the refiner 1 to refine the crystal. The refined crystal is taken out from an outlet 4 provided at an upper part of the refiner 1. An agitator 2 of the refiner 1 is provided with a rotatable shafts 2A having agitating fins 2B, unraveling and making the crystal supplied from the inlet 3 flow upwardly.

[0028] Either type of crude cyclic esters can be refined by either type of refiners. How to refine the two types of crude cyclic esters using either of the refiners in Figs. 1 and 2 will be described.

The Cyclic Ester Having No Solvent

[0029] The cyclic ester crystal obtained by depolymerizing a hydroxycarboxylic oligomer is successively supplied to the refiner 1 from the inlet 3 by the supplying means such as the screw conveyor. The supplied crystal is agitated by the agitating fins 2B and flows upwardly inside the refiner 1. A part of the crystal turns to a downflowing melted liquid together with the melted cyclic ester, which is melted by the melting heater 14 or supplied from the outside by the melted liquid supplying means 5. The downflowing melted liquid is brought into counterflow-contact with the upflowing crude cyclic ester crystal to clean off the impurities adhered to the surface of the crystal and sweat out the impurities caught inside the crystal, thus refining the crude cyclic ester. The refined crystal is taken out from the outlet 4, and the removed impurities are exhausted from the impurity outlet 7 through the filter 6.

The Cyclic Ester Having High-boiling Point Organic Solvent Adhered thereto

[0030] The cyclic ester crystal having a high-boiling point organic solvent adhered thereto is obtained by depolymerizing and distilling a hydroxycarboxylic oligomer with the high-boiling point organic solvent, cooling a distilled product at a temperature lower than the melting point of the cyclic ester, and separating the thus produced product, which comprises the cyclic ester crystal and a slurry of the high-boiling point organic solvent, into a solid and a liquid. The thus obtained cyclic ester crystal

is supplied from the inlet 3 by the supplying means such as the screw conveyor. It is preferable that the content of the cyclic ester crystal in the supplied substances is more than 50%. The supplied crystal is agitated by the agitating fins 2B and flows upwardly inside the refiner 1. A part of the crystal turns to a downflowing melted liquid together with the melted cyclic ester, which is melted by the melting heater 14 or supplied from the outside by the melted liquid supplying means 5. The downflowing melted liquid is brought into counterflow-contact with the upflowing crude cyclic ester crystal to clean off the impurities adhered to the surface of the crystal and sweat out the impurities caught inside the crystal, thus refining the crude cyclic ester. The refined crystal is taken out from the outlet 4 and removed impurities are exhausted from the impurity outlet 7 through the filter 6.

Example

[0031] As an example, 18.3 kg/hour of a glycolide having a purity rate of 99.99% is obtained by supplying 22.1 kg/hour of a mixture comprising 91.1 mass % of a glycolide and 8.9 mass % of dibutyl phthalate having a boiling point of 340°C to the refiner 1 shown in Fig. 2, which has two cylinders each having an internal diameter of 75 mm and a height of 2000 mm.

[0032] As the present invention has steps of: supplying said crude cyclic ester to a vertically extending cylindrical refiner from an inlet provided at a lower part of said refiner; agitating said crude cyclic ester by an agitator provided in said refiner to make said crude cyclic ester flow upwardly; refining said crystal of said crude cyclic ester by counterflow-contact between said upflowing crude cyclic ester and a downflowing melted liquid which contains a refined crystal component; and taking out said refined crystal of said crude cyclic ester from an outlet provided at an upper part of said refiner, the present invention brings the following advantages.

(1) No additional solvent or cleaning liquid for the refining process is required, unlike a conventional refining method.

(2) Since no additional solvent or cleaning liquid is used, the refining equipment is simplified. That is, various processes including cleaning of the high-boiling point organic solvent, evaporation and separation of the high-boiling point organic solvent and the cleaning liquid, drying of removing the cleaning liquid adhered to the refined crystal, cooling and collecting of the cleaning liquid discharged from the drying equipment are not required. Accordingly, many machines and ancillary facilities such as a pump, storage tank, and pipe are not necessary. In addition, electricity, steam, and cooling water are saved.

(3) Even if impurities are caught inside the crystal, and a plurality of times of re-crystallization are required under the conventional method, highly pure

crystal is produced by the invention.

(4) Since the steps of the whole process are successively operated, the operation control is easy.

(5) The manufacturing cost is reduced.

5

Claims

1. A method of refining a crystal of cyclic ester, comprising the steps of:

10

supplying a crude cyclic ester to a vertically extending cylindrical refiner (1) from an inlet (3) provided at a lower part of said refiner (1);

agitating said crude cyclic ester by an agitator (2) provided in said refiner (1) to make said crude cyclic ester flow upwardly;

15

refining said crystal of said crude cyclic ester by counterflow-contact between said upflowing crude cyclic ester and a downflowing melted liquid which contains a refined crystal component; and

20

taking out said refined crystal of said crude cyclic ester from an outlet (4) provided at an upper part of said refiner (1).

25

2. The method of refining a crystal of cyclic ester according to claim 1, wherein said melted liquid which contains a refined crystal component is supplied at the upper part of the refiner (1) from the outside thereof.

30

3. The method of refining a crystal of cyclic ester according to claim 1 or Claim 2, wherein at least one high-boiling point organic solvent having a boiling point greater than a melting point of said crystal of said crude cyclic ester is adhered to said crystal of said crude cyclic ester.

35

4. The method of refining a crystal of cyclic ester according to any one of claims 1-3, wherein said cyclic ester is a hydroxycarboxylic acid cyclic ester.

40

5. The method of refining a crystal of cyclic ester according to claim 4, wherein said hydroxycarboxylic acid cyclic ester is a glycolic acid dimeric cyclic ester.

45

50

55

Figure 1




Figure 2

